

Product Information

TROGAMID® Care MX97

MICROCRYSTALLINE AND TRANSPARENT POLYAMIDES FOR FOR MEDICAL APPLICATION



TROGAMID® Care MX is the material of choice for all applications dealing with pharmaceutical formulations, lipids or aggressive disinfectants, since it exhibits an exceptional resistance towards chemicals and stress-cracking. Examples include fluid and drug delivery equipment such as stop-cocks, dialyzer parts, housings, covers or hearing aids.

Target areas of application for TROGAMID® Care MX compounds include fluid and drug delivery systems, surgical instruments, housings, monitoring and imaging devices and durable medical equipment.

All advantages at a glance

- High transparency
- High chemical resistance
- Very good stress crack resistance
- UV resistance
- High dynamic load-bearing capacity
- High impact resistance
- Easy processability & colorability
- Free of BPA
- Gamma and EtO sterilizable

Biocompatibility of TROGAMID® Care

TROGAMID® Care grades were tested on biocompatibility for applications within the body of up to 30 days contact time and comply with USP <88> class VI and ISO 10993 standards.

Biocompatibility tests for TROGAMID® Care:

Processing of TROGAMID® Care

For information about processing of TROGAMID®, please follow the general commendations about "[Processing of TROGAMID® compounds](#)".

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM
OR VISIT OUR PRODUCT AT WWW.EVONIK.COM/MEDICAL-TECHNOLOGY

Mechanical properties ISO

	dry / cond	Unit	Test Standard
Tensile Modulus	1400 / -	MPa	ISO 527
Tensile Strength	60 / -	MPa	ISO 527
Yield stress	60 / -	MPa	ISO 527
Yield strain	8 / -	%	ISO 527

Stress at 50% strain	42 / -	MPa	ISO 527
Stress at break	65 / -	MPa	ISO 527
Nominal strain at break, ϵ_B	>50 / -	%	ISO 527
Charpy impact strength, +23°C	N / -	kJ/m ²	ISO 179/1eU
Charpy impact strength, 0°C	N / -	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	14 / 10.5	kJ/m ²	ISO 179/1eA
Type of failure	C / C	-	-
Charpy notched impact strength, 0°C	14 / -	kJ/m ²	ISO 179/1eA
Type of failure	C / -	-	-
Charpy notched impact strength, -30°C	13 / -	kJ/m ²	ISO 179/1eA
Type of failure	C / -	-	-
Flexural modulus, 23°C	1700 / -	MPa	ISO 178
Flexural stress at conv. deflection, 23°C	50 / -	MPa	ISO 178
Flexural strain at flexural strength, 23°C	9 / -	%	ISO 178
Flexural strain at break, 23°C	N / -	%	ISO 178

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature	250 / *	°C	ISO 11357-1/-3
Glass transition temperature	140 / *	°C	ISO 11357-1/-2
Temp. of deflection under load A, 1.80 MPa	108 / *	°C	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	122 / *	°C	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	135 / *	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	130 / *	°C	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	90 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, 23°C to 55 °C, normal	90 / *	E-6/K	ISO 11359-1/-2
Melting Temperature	250	°C	ASTM D 3418

Physical properties	dry / cond	Unit	Test Standard
Water absorption	3.5 / *	%	Sim. to ISO 62
Humidity absorption	1.5 / *	%	Sim. to ISO 62
Density	1020 / -	kg/m ³	ISO 1183
Shore D hardness	81 ^[b] / -	-	ISO 7619-1
Density	1020	kg/m ³	ASTM D 792

b: 3 seconds

Burning Behav.	dry / cond	Unit	Test Standard
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
Relative permittivity, 100Hz	3.6 / -	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.2 / -	-	IEC 62631-2-1
Dissipation factor, 100Hz	120 / -	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	325 / -	E-4	IEC 62631-2-1
Electric strength, AC, S20/P50	27 / -	kV/mm	Sim. to IEC 60243-1
CTI, test solution A, 50 drops value	600 / -	-	IEC 60112

Rheological properties	dry / cond	Unit	Test Standard
Melt volume-flow rate, MVR	31 / *	cm ³ /10min	ISO 1133
Temperature	285 / *	°C	-
Load	5 / *	kg	-
Molding shrinkage, parallel	0.7 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577

Characteristics

Key Feature, Industrial Sector

Medical

Key Feature, Processing

Injection Molding, Extrusion

Key Feature, Optics

Transparent

Key Feature, Resistance to

U.V. / Light / Weathering

Key Feature, Certificate / Licence

Food contact, Medical Application

Key Feature, Additives

Release agent, Unfilled

Processing

Film Extrusion, Profile Extrusion, Sheet Extrusion

Special Characteristics

halogen-free, Semi-crystalline, Environmental Stress Crack Resistance, U.V. stabilized

Ecological valuation

US Pharmacopeia Class VI Biocompatibility

Additives

Release agent, Processing aids

Delivery form

Pellets, Granules

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

® is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
 45772 Marl / Germany
 Tel: +49 2365 49-9878
evonik-hp@evonik.com
www.plastics-database.com